



Consumer and
Corporate Affairs Canada

Consumption
of Corporations Canada

(11) (A) No. 1 198 558

(45) ISSUED 851231

(52) CLASS 9-36

(51) INT. CL. D21C 3/02

(19) (CA) **CANADIAN PATENT** (12)

(54) Method for Controlling the Properties of White Liquor

(72) Bertelsen, Per M.,
Denmark

(73) Granted to Kemotron A/S
Denmark

(21) APPLICATION No. 412,133

(22) FILED 820924

(30) PRIORITY DATE Denmark (4242/81) 810925

No. OF CLAIMS 55

Canada

DISTRIBUTED BY THE PATENT OFFICE, OTTAWA
CCA274 (11-83)



1198558

The present invention relates to a process for controlling the properties of white liquor used by the preparation of boiling liquor for use in the sulphate process, the electric conductivity of the liquor being measured by said process after the causticization.

By the so-called kraft process or sulphate process pulp is prepared by digesting chips of wood in a strongly alkaline liquor mainly containing NaOH and Na₂S. During the pulping, the content of NaOH of the liquor is consumed, said content being relatively high at the beginning, whereas its content of Na₂S remains substantially unchanged.

The spent pulping liquor is called black liquor and contains, inter alia, the dissolved lignin in addition to the residue chemicals. The black liquor is concentrated and subsequently burnt in a steam boiler, whereby its content of energy is utilized. In the bottom of the boiler, the combustion products are collected in the form of a melt mainly consisting of Na₂S and Na₂CO₃.

The melt is introduced into a tank with water (thin liquor), wherein it is dissolved. The resulting liquor is called green liquor. The green liquor always contains a small amount of NaOH which may vary a great deal. The green liquor is characterized by having a high content of Na₂CO₃ and a small amount of NaOH. In order to re-form the boiling liquor burnt lime is added to the green liquor in a slaker, in which the following reactions take place:



The reactions proceed in parallel towards a state of equilibrium and are more or less displaced to the right. The liquor formed by the causticization is called white liquor.

- 5 The content of Na_2S of the green liquor does not take part in the process, but is retrieved in the white liquor. When the amount of water consumed by the reaction 1) is ignored (about 2%), the content of Na_2S of the white liquor is equal to the content of Na_2S of the green liquor.
- 10 In order to permit a completion of the processes, the liquor is transferred from the slaker to the first of a row of causticizers with stirring. The contents of the first causticization vessel or causticizer are transferred into the next vessel and so on until an overflow is established by
- 15 the causticizers being positioned in gradually lower heights. The number of causticizers may vary.

- Upon termination of the reaction, the causticized liquor (white liquor) is separated from the calcareous silt. Subsequently, the white liquor is used, optionally after
- 20 additional clarifying, for the preparation of a new pulping liquor. The white liquor and consequently the pulping liquor always contain a small amount of unreacted Na_2CO_3 . The white liquor is characterized by containing a high amount of NaOH and a small amount of Na_2CO_3 . The calcareous silt is flushed
- 25 for liquor residues, dehydrated, and burnt in a rotary kiln whereby the calcium oxide (burnt lime) necessary for the causticization is re-formed. The wash water is called thin liquor

and is utilized in the dissolving tank for the melt formed from the black liquor, whereby the content of liquor residues of the thin liquor is reused.

As it will appear, the chemicals circulate in two circuits, viz. one for the sodium (the digesting process - the evaporation - the combustion - the dissolving - the separation from the white liquor - the washing out - the dehydration - the burning). The unavoidable loss of chemicals is as far as the sodium is concerned replaced by addition of Na_2SO_4 to the concentrated black liquor. At the combustion, the major part is reduced to Na_2S , which results in the name the sulphate process. A small amount of NaOH may furthermore be added to the white liquor. As far as the calcium is concerned, burnt lime CaO may be added at the outlet 15 of the rotary kiln, or lime CaCO_3 may be added at the inlet of the rotary kiln.

The white liquor and the green liquor may be characterized by some quantities, the definition of which is recommended to be used by central laboratories of which for wood 20 or paper pulp in Scandinavia, and which for instance are mentioned in SCAN-N 2:63, whereby the statement of the various chemical substances is to be understood as the concentration of the compound in question, calculated as g of NaOH/l :

Active alkali AA = $\text{NaOH} + \text{Na}_2\text{S}$

25 Efficient alkali EA = $\text{NaOH} + 0.5 \text{Na}_2\text{S}$

Total alkali = all alkali salts.

Total titratable alkali TTA = $\text{NaOH} + \text{Na}_2\text{S} + \text{Na}_2\text{CO}_3$

The degree of causticization (in white liquor)

$$C = \frac{\text{NaOH}}{\text{NaOH} + \text{Na}_2\text{CO}_3} \times 100\%$$

The sulphidity (in white liquor)

$$S = \frac{\text{Na}_2\text{S}}{\text{NaOH} + \text{Na}_2\text{S}} \times 100\%$$

5 The degree of reduction (in green liquor)

$$R = \frac{\text{Na}_2\text{S}}{\text{Na}_2\text{SO}_4 + \text{Na}_2\text{S}} \times 100\%$$

Furthermore the following can be mentioned:

The carbonate conversion: $\text{Na}_2\text{CO}_{3\text{Gr}} - \text{Na}_2\text{CO}_{3\text{Hv}}$ g/l

The degree of the carbonate conversion:

10
$$\frac{\text{Na}_2\text{CO}_{3\text{Gr}} - \text{Na}_2\text{CO}_{3\text{Hv}}}{\text{Na}_2\text{CO}_{3\text{Gr}}} \times 100\%$$

The control of the causticization process may choose the calcium cycle, the sodium cycle or both the calcium cycle and the sodium cycle as starting point.

As far as the sodium cycle is concerned, the difficult steps in the process are centred about the combustion of the concentrated black liquor and the causticization process. By the causticization particularly the control of the addition of burnt lime is difficult. This is partly due to the great time lag between the addition of quicklime and the filtration (2-3 hours) of the finished liquor, partly

15
20

due to the variability of the burnt lime both with respect to its reactivity (the slaking velocity) and with respect to its content of active lime. However, the difficulty in controlling the addition of burnt lime especially depends on the fact that it has not previously been possible continuously to measure or determine process relevant parameters to be used for the required control.

Previously, the causticization process was often controlled by means of manual regulation of the feeding of burnt lime on the basis of laboratory analyses of the white liquor immediately after the slaker and optionally of the green liquor, whereby it was tried to maintain the degree of causticization (in the white liquor) at a predetermined value. This procedure is encumbered with the drawback that it is necessary to wait so long for the result of the analysis that in general it is too late to establish the necessary restoration of the causticization process. Attempts to restore the causticization process may easily involve for instance undue calcareous concretion causing a poorer filtratability and a too high content of calcium in the white liquor whereby filters, pipes, pumps, boilers etc. are calcified, cf. K. Kinzner "Untersuchungen zur Kaustizierung von Grünlaugen", in Proceedings of the Symposium in Recovery of Pulp Chemicals, Helsinki 1968, page 279. By keeping the specific gravity and consequently the TTA-value of the green liquor constant, it is possible to in-

fluence the causticization process positively concerning keeping of the degree of causticization. However, it is not possible to take into account the considerable variation of the quality of the lime by keeping the specific gravity of the green liquor. In addition, the composition of the green liquor may vary considerably irrespective of the fact that the specific gravity and consequently the TTA-value are kept constant. The content of NaOH of the green liquor may for instance vary considerably depending on the amount of water which it is necessary to add to the dissolving tank in addition to the thin liquor in order to dissolve the melt resulting from burning of the concentrated black liquor.

It is known to control the causticization process by means of an automatic titrator for the determination of the content of Na_2CO_3 in the green liquor and the white liquor, two temperature measurements being simultaneously performed, viz. a temperature measuring of the green liquor immediately before the slaker and a temperature measuring of the contents of the slaker. The slaking (process 1) involves generation of heat, whereas the causticization (process 2) involves no significant heat content change. The rise in temperature of 10-15°C renders it possible to calculate the amount of calcium hydroxide available for the causticization. This calculation renders it possible to control the addition of burnt lime said control being performed in preparation for a constant

1198558

degree of causticization. An automatic titrator is, however, expensive and must be kept up with analysis reagents, cleaned, and altogether controlled with respect to its function, and it uses time for performing an analysis. The 5 measurings achieved are therefore delayed relative to the moment the necessary control signals should have been given. Consequently, these measurings and the registration thereof cannot be considered on-line. The rise in the temperature measured is relatively modest, and in order to achieve an 10 accurate figure of the amount of calcium hydroxide available for the causticization, the temperatures must be measured individually with great accuracy.

By another known measuring method, the conductivity of the white liquor measured after the slaker is used as a measurement of the degree of causticization, and this measurement is made the basis of the control of the amount of added burnt lime. However, the electric conductivity of a solution depends on all the electrolytes present in the electrolytic solution in question, on their concentration, and on the 20 temperature, since in practice it is always necessary to temperature compensate a conductivity measuring to some reference temperature. The conductivity of the white liquor depends not only on the composition of the liquor concerning NaOH or Na_2CO_3 (the degree of causticization), but also on 25 the content of Na_2S , and the concentration is of particular importance. Therefore a measuring of the conductivity solely

of the white liquor does not permit a good determination of a parameter, on which it is possible to base a control of the degree of causticization.

As it is known, an aqueous solution of NaOH possesses a much higher conductivity than an aqueous solution of Na_2CO_3 having the same concentration. An aqueous solution of Na_2S having the corresponding concentration possesses a conductivity between the conductivity measured for the NaOH and the Na_2CO_3 solution, respectively.

Furthermore the solution having the highest amount of NaOH among the aqueous solutions of mixtures of electrolytes containing NaOH, Na_2S , and Na_2CO_3 possesses the highest conductivity provided the content of Na_2S is constant, the sum of the amounts of substance of said solutions being equal, e.g. calculated as g of NaOH/l or as g of Na_2O /l.

Concerning a green liquor and the white liquor derived therefrom by causticization, the sum of the amounts of electrolytes, calculated as g of NaOH/l, is equal in the green liquor and in the white liquor, the content of Na_2S not being influenced by the causticization process. Since the white liquor contains more NaOH than the green liquor from which it is derived, it also possesses a higher conductivity than the green liquor, and this recognition is the basis of the invention.

The process according to the invention is characterized by measuring the electric conductivity of the green liquor before the causticization in addition to the measuring of the conductivity of the white liquor.

1198558

Thus, by measuring the conductivity of the green liquor both before the slaker and gradually as it passes through the slaker, it is possible to achieve a unique picture of the causticization process. The second conductivity measuring is in practice performed either within the slaker or immediately thereafter, in which connection it should be noted that an efficient stirring is maintained within the slaker.

The conductivity of the white liquor immediately after the slaker is about half as much as the conductivity of the green liquor. Tests have lead to the recognition that the amount of this increase is proportional to the instant degree of the reaction of Na_2CO_3 into NaOH , and that the amount of the increase is independent of the content of Na_2S and depends only to a minor degree on the total content of chemicals (TTA) of the green liquor. The conversion of Na_2CO_3 into NaOH from one point to another in the process is therefore measureable by a difference measuring of the conductivity by means of two conductivity meters. The high relative increase in the conductivity ensures a very accurate determination of the carbonate conversion.

It turned out surprisingly, that it is possible to tabulate a formula expression in the form of a fraction, the conductivity of the green liquor and of the white liquor forming part of the numerator, and the TTA-value forming part of an expression of the second degree in the denominator:

1198558

$$\frac{\kappa_{Hv} - \kappa_{Gr}}{f_1(TTA)}$$

where $f_1(TTA) = 4.694 \cdot 10^{-5} \cdot TTA^2 - 2.652 \cdot 10^{-2} \cdot TTA + 7.335 \left(\frac{mS/cm}{g/l} \right)$

The TTA of the green liquor forms part of the resulting expression, but since the variation therein have a relatively minor influence on the accuracy, a TTA-value obtained by measuring an arbitrary parameter is satisfactory, said parameter correlating with the TTA-value to a sufficiently high degree.

10 The specific gravity turned out for instance to meet said condition, and a preferred embodiment of the process according to the invention is therefore characterized by determining the TTA-value (total titratable alkaline), preferably by measuring the specific gravity of the green
15 liquor or the absorption of a gamma radiation by the green liquor.

As in the following formulae, the formula of the carbonate conversion is a formula of general application at other temperatures than the temperature actually present
20 provided the conductivities κ_{Gr} and κ_{Hv} measured are temperature compensated to an appropriate reference temperature $t^\circ C$. The preferred reference temperature is $90^\circ C$, and the formulae thus apply by the use of a reference temperature within a predetermined range about $90^\circ C$.

1198538

According to a further embodiment of the invention, the quantities characteristic for the production plant, preferably \underline{x} and \underline{y} , are determined by means of chemical analysis of the green liquor and the white liquor, whereby

5 \underline{x} is the ratio of the content of Na_2S to the content of Na_2CO_3 in the green liquor, both parts being calculated as g of NaOH/l, and whereby \underline{y} is the ratio of the content of Na_2S in the white liquor, calculated as g of NaOH/l, to TTA.

10 Instead of the above ratios \underline{x} and \underline{y} , it is possible to use arbitrary ratios of the content of NaOH, Na_2S , Na_2CO_3 and TTA of the green liquor and of the white liquor, respectively, depending on what has shown to be most appropriate based on measurements of working on the plant in question.

15 A formula expression can be set up, in which the conductivity of the green liquor forms part, whereby the content thereof of Na_2CO_3 can be calculated by inserting the numerical value from a measuring of the conductivity and the TTA-value determined by measuring the specific gravity:

$$20 \quad \text{Na}_2\text{CO}_3, \text{Gr} = \frac{f_2(\text{TTA}) - \mu_G}{f_1(\text{TTA}) + x + f_3(\text{TTA})}$$

where $f_2(\text{TTA}) = -1.158 \cdot 10^{-2} \cdot \text{TTA}^2 + 6.939 \cdot \text{TTA} + 192.6 \text{ (mS/cm)}$

$f_3(\text{TTA}) = 5.307 \cdot 10^{-5} \cdot \text{TTA}^2 - 2.030 \cdot 10^{-2} \cdot \text{TTA} + 3.512 \text{ (} \frac{\text{mS/cm}}{\text{g/l}} \text{)}$

Tests have shown that the ratio of the content of Na_2S to Na_2S to Na_2CO_3 of the green liquor with a sufficiently good approximation can be equalized with a constant value \underline{x} characteristic of the causticizing plant in question under the prevailing operational conditions so that the numerical value thereof can be inserted in the formula expression.

Similarly a formula expression can be set up, in which the conductivity of the white liquor forms part, whereby the content hereof of NaOH can be calculated by inserting the numerical value from a conductivity measuring as well as the TTA-value obtained by measuring the specific gravity:

$$\text{NaOH} = \frac{\mu_{\text{HV}} \cdot \underline{y} \cdot f_4(\text{TTA}) - f_5(\text{TTA})}{f_1(\text{TTA})}$$

$$\begin{aligned} f_4(\text{TTA}) &= -6.129 \cdot 10^{-6} \cdot \text{TTA}^3 + 6.226 \cdot 10^{-3} \cdot \text{TTA}^2 + \\ &\quad 3.823 \cdot \text{TTA} \text{ (mS/cm)} \\ f_5(\text{TTA}) &= 2.754 \cdot 10^{-5} \cdot \text{TTA}^3 - 1.618 \cdot 10^{-2} \cdot \text{TTA}^2 + \\ &\quad 3.877 \cdot \text{TTA} \text{ (mS/cm)} \end{aligned}$$

Tests have shown that the ratio of the content of Na_2S of the white liquor to the TTA-value with sufficiently good approximation can be equalized with a constant value \underline{y} characteristic of the causticizing plant in question under the prevailing operational conditions so that the numerical value thereof can be inserted in the formal expression.

1198558

These measurements render it possible to calculate the carbonate conversion, the content of Na_2CO_3 of the green liquor, the content of NaOH of the white liquor, the degree of carbonate conversion, the causticizing degree of the
5 white liquor, the sulphidity of the white liquor, the content of active alkali of the white liquor, and/or the content of efficient alkali of the white liquor, and the properties of the white liquor are subsequently controllable on the basis thereof.

10 Commercially accessible, industrial conductivity meters (e.g. for measuring in accordance with the 4-electrode principle) are today available for the measurements of the electric conductivity. These conductivity meters measure very accurately also in media in which a heavy calci-
15 fication of the measuring cell must be anticipated. Such conductivity meters are sturdy and accurately measuring instruments which have gained a footing within the industry, and which do not require particular tending or keeping up in the form of providing with
20 reagents as for instance in case of a titrator. Such conductivity meters have very short response times and transmit a continuous signal which can be used advantageously for automatic control.

By the process according to the invention, the mea-
25 suring signals can be used for the control of the properties of the white liquor by regulating the amount of burnt lime introduced into the slaker, by regulating the amount of

1198558

green liquor transferred into the slaker, and/or by
regulating the TTA-value of the green liquor. Conse-
quently the properties of the white liquor are controlled
at the same time as the amount of white liquor can be
5 changed in response to the requirements.

For this purpose a data processor is preferably
used for on-line registration of the measuring values,
for the calculation of the change required of the amount
of burnt lime added to the slaker per time unit, and/or
10 for the calculation of the change in question of the
amount of green liquor fed to the slaker per time unit,
and/or for the calculation of the required change of the
TTA-value of the green liquor concerning the control of
said added amounts or of the TTA-value.

15 When the process does not pass off in the steady
state, its dynamics must be considered, the values of
TTA and κ_{Gr} then to be inserted in the formulae must be
the values registered on that point in the process where
 κ_{Hv} is measured if no causticization took place (no addi-
20 tion of CaO). According to a preferred embodiment of the
invention, a small partial flow of the green liquor is re-
moved and transferred to a measuring vessel with stirring
and similar to the slaker in such a manner that the volume
ratio of the slaker to the measuring vessel is equal to the
25 ratio of the respective amounts of green liquor fed thereto,
whereby conductivity measuring and/or a TTA-determination
are performed on a corresponding place in the measuring

1198558

vessel as in the slaker. In this manner the conductivity and the TTA-value of the green liquor measured in the measuring vessel adapted thereto are immediately usable in the formulae as the values aimed at. Nothing, however, prevents said value from being measured directly in the green liquor fed to the slaker, as well as nothing prevents the time lag and "the admixing" from being subsequently simulated by means of calculatable methods to obtain the values aimed at of the conductivity and the TTA in green liquor. Such a simulation of the time lag and the admixing is preferred since it is easily adjustable to the particular mode of operation of various industrial installations.

In the general case the calculation of the carbonate conversion thus involves the use of a model of the process whereby the time lag and the admixing of the green liquor entering the slaker are considered. This calculation is, of course, carried out by means of the computer system used for on-line registration of the measurements.

20 Since the causticization process is not fully completed within the slaker, only 70-80% of the reaction taking place within the slaker, and the remaining 20-30% of the reaction taking place in the causticizers, it is by measuring in three or several places possible to provide a still better picture of the passing off of the process.

1198558

Especially by measuring the conductivity of the white liquor after separation of the calcareous silt, it is possible to obtain information on the state of the finished liquor for the following preparation of the pulping liquor.

By the process according to the invention it is therefore advantageous to perform the measuring of the conductivity after termination of the causticization within the slaker or the discharge part thereof (the classifier), and/or within one or more of the following causticizers or the outlet conduits thereof and/or within the clarified white liquor.

In this manner the control system used can be adapted to the use of so-called tuning, whereby measuring of the conductivity of the white liquor on two places within the causticizers is compared with the measurement of the conductivity and the TTA-value of the green liquor. The relevant process parameters on the two measuring places are calculated by using dynamic models corresponding to the two places for measuring the conductivity of the white liquor. These white liquor parameters are subsequently applicable for providing a better basis of determination for the operator at manual control or for providing a better basis of determination for the change of the set

-value at a PID-regulation (proportional integral differential regulation) or for up-dating the control parameters in a control system in order to optimize the properties of the finished white liquor.

The invention will be described below with reference to the accompanying drawing and an example.

The drawing is a diagrammatic view of a causticizing plant used in the sulphate process.

10 Green liquor 1 is formed by dissolving the melt from the combustion of black liquor after concentration, in water and thin liquor, is transferred into a slaker 2 in which slaking and causticization are carried out during addition of burnt lime. The resulting precipitate deposited in the classifier is carried out of the slaker by means of a worm conveyor, whereas the content of the slaker of milk of lime passes to causticizers 3, 4 and 5 through overruns. From the last causticizer, the white liquor is carried together with calcareous silt to a separating and washing filter 6. From this filter the filtrated white liquor continues to a storage tank (not shown) via line 7. The washed
20 calcareous silt is transferred into a vessel 8 and further to a dehydration filter 9. Subsequently, the calcareous silt is carried to a rotary kiln for burning, whereby supplementing lime (not burnt) can be added immediately before the rotary kiln 10 at 14. The burnt lime which can be supplemented with burnt lime 13 is transferred to a lime silo 11, a conveyor mechanism 12 for the lime being situated below said silo.

This conveyor mechanism 12 carries the burnt lime into the slaker 2.

The process variables mentioned in the following example are for instance desired to be determined on two places in the causticizing plant, place A and place B referred to as 15 and 16, respectively. A flowmeter 17, a densimeter 18 (measuring the TTA-value), a conductivity meter 19 (green liquor), a conductivity meter 20 (white liquor immediately after the slaker), and a conductivity meter 21 (the completed white liquor) are used for this purpose.

The delayed values of TTA and the conductivity of the green liquor are calculated in a calculation unit 22, and the signals in question are transferred to calculation unit 23 and 25 also supplied with the signals from the conductivity meters 20 and 21, respectively. On the places A and B, the process variables are calculated in the calculation units 23 and 25, and based on these variables control signals 24 and 26 are generated and are transmitted for the desired control of added amount of burnt lime per time unit, added amount of green liquor per time unit or the TTA-value in the green liquor.

Example

In a paper pulp producing plant, the following measurements were carried out in the causticizing plant after a long period of steady state, whereby comparison with laboratory analyses can be carried out:

1198558

$$\kappa_{Gr}, 90^{\circ}C = 498.0 \text{ mS/cm}$$

$$\kappa_{HV}, 90^{\circ}C = 723.3 \text{ mS/cm}$$

$$Vf_{90^{\circ}C} = 1.135 \text{ kg/l} - TTA = 142.2 \text{ g/l}$$

The quantities \underline{x} and \underline{y} characteristic of the process
5 are found from the average value of 9 weeks' laboratory
analyses as follows:

$$x = \frac{Na_2S_{Gr}}{Na_2CO_3Gr} = 0.2772$$

$$y = \frac{Na_2S_{HV}}{TTA} = 0.1677$$

In the following, all the concentrations of substance
10 have been stated as g of NaOH/l. The connection between
specific gravity (90°C) and TTA was found to be:

$$TTA = Vf_{90} \cdot 962.2 - 949.9 \text{ (g/l)}$$

$$R = 92\%$$

whereby the specific gravity at 90°C and the figures 962.2
15 and 949.9 are obtained by means of a row of measurements of
the specific gravity and corresponding chemical analyses
for the determination of the TTA-value based on linear
regression, and R is the correlation factor.

1198558

1) Carbonate Conversion

$$\text{carbonate conversion} = \frac{K_{Hv} - K_{Gr}}{f_1(TTA)}$$

$$\text{where } f_1(TTA) = 4.694 \cdot 10^{-5} \cdot TTA^2 - 2.652 \cdot 10^{-2} \cdot TTA + 7.335 \left(\frac{\text{mS/cm}}{\text{g/l}} \right)$$

Illustrated with figures:

$$5 \quad \text{carbonate conversion} = \frac{723.3 - 498.0}{4.513} = \underline{\underline{49.9 \text{ g/l}}}$$

2) Na₂CO₃ in green liquor

$$\text{Na}_2\text{CO}_3, \text{Gr} = \frac{f_2(TTA) - u_G}{f_1(TTA) + x \cdot f_3(TTA)}$$

$$\text{where } f_2(TTA) = -1.158 \cdot 10^{-2} \cdot TTA^2 + 6.939 \cdot TTA + 192.6 \left(\frac{\text{mS/cm}}{\text{g/l}} \right)$$

$$10 \quad f_3(TTA) = 5.307 \cdot 10^{-5} \cdot TTA^2 - 2.030 \cdot 10^{-2} \cdot TTA + 3.512 \left(\frac{\text{mS/cm}}{\text{g/l}} \right)$$

Illustrated with figures:

$$\text{Na}_2\text{CO}_3, \text{Gr} = \frac{245.2 - 498.0}{4.513 + 0.2772 \cdot 1.6985} = \underline{\underline{89.7 \text{ g/l}}}$$

1198558

3) NaOH in white liquor

$$\text{NaOH} = \frac{\mu_{\text{HV}} - Y \cdot f_4(\text{TTA}) - f_5(\text{TTA})}{f_1(\text{TTA})}$$

$$f_4(\text{TTA}) = -6.129 \cdot 10^{-6} \cdot \text{TTA}^3 - 6.226 \cdot 10^{-3} \cdot \text{TTA}^2 + 3.823 \cdot \text{TTA} \text{ (mS/cm)}$$

$$5 \quad f_5(\text{TTA}) = 2.754 \cdot 10^{-5} \cdot \text{TTA}^3 - 1.618 \cdot 10^{-2} \cdot \text{TTA}^2 + 3.877 \cdot \text{TTA} \text{ (mS/cm)}$$

Illustrated with figures:

$$\text{NaOH} = \frac{723.3 - 0.1677 \cdot 400.1 - 303.3}{4.513} = 78.2 \text{ g/l}$$

4) Degree of Carbonate Conversion

$$10 \quad \frac{\text{Carbonate conversion}}{\text{Carbonate in green liquor}} \cdot 100\% = \frac{49.9}{89.7} \cdot 100\% = 55.7\%$$

5) Causticizing degree of white liquor

$$\text{C\%} = \frac{\text{NaOH}_{\text{HV}}}{\text{Na}_2\text{CO}_3, \text{Gr} - \text{carbonate conversion}}$$

$$\text{C\%} = \frac{78.2}{89.7 - 49.9 + 78.2} \cdot 100\% = 56.3\%$$

1198558

6) The sulphidity of white liquor

$$S\% = \frac{Na_2S_{HV}}{NaOH_{HV} + Na_2S_{HV}} \cdot 100\%$$

$$Na_2S_{HV} = TTA - NaOH_{HV} - Na_2CO_{3HV}$$

$$Na_2CO_{3HV} = Na_2CO_{3,Gr} - \text{carbonate conversion}$$

5 providing

$$S\% = \frac{TTA - NaOH_{HV} - Na_2CO_{3,Gr} + \text{carbonate conversion}}{TTA - Na_2CO_{3,Gr} + \text{carbonate conversion}}$$

Illustrated with figures:

$$S\% = \frac{142.2 - 78.2 - 89.7 + 49.9}{142.2 - 89.7 + 49.9} \cdot 100\% = \underline{23.6\%}$$

7) Active alkali in white liquor

$$10 \text{ AA} = NaOH_{HV} + Na_2S_{HV}$$

$$= TTA - Na_2CO_{3HV} = TTA + Na_2CO_{3,Gr} - \text{carbonate conversion}$$

Illustrated with figures:

$$\underline{AA} = 142.2 + 49.9 - 89.7 = \underline{102.4 \text{ g/l}}$$

1198558

8) Efficient alkali in white liquor

$$EA = NaOH_{HV} + 1/2 Na_2S_{HV}$$

$$= NaOH_{HV} + 1/2 (TTA - NaOH_{HV} - Na_2CO_{3HV})$$

$$= 1/2 (NaOH_{HV} + TTA - NaCO_{3,Gr} + \text{carbonate conversion})$$

Illustrated with figures:

5 $EA = 1/2 (78.2 + 142.2 - 89.7 + 49.9) = \underline{20.3 \text{ g/l}}$

1198558

THE EMBODIMENTS OF THE INVENTION IN WHICH AN EXCLUSIVE PROPERTY OR PRIVILEGE IS CLAIMED ARE DEFINED AS FOLLOWS:

1. A process for controlling the causticization process in the causticization step of the sulphate process and, consequently, the composition of the white liquor used by the preparation of boiling liquor in the sulphate process, wherein the electrical conductivity of the white liquor is measured after termination of the causticization step; the improvement in said process comprising: additionally measuring the electrical conductivity of the green liquor before the causticization step, and using the conductivity measurements to calculate the characteristic numeric values of the composition of the white liquor, wherein said values are used to control the causticization process.

2. A process as claimed in claim 1, wherein the improvement additionally comprises: determining the total titratable alkali value of the green liquor.

3. A process as claimed in claim 2, wherein the total titratable alkali value is obtained by measuring the specific gravity of the green liquor or the gamma radiation absorption of the green liquor.

4. A process as claimed in claim 2, wherein the improvement additionally comprises: determining quantities characteristic for a production plant used in said process.

5. A process as claimed in claim 3, wherein the improvement additionally comprises: determining quantities characteristic for a production plant used in

mab/

25

1198558

said process.

6. A process as claimed in claim 4 or 5, wherein said quantities are x and y obtained by means of chemical analysis of the green and white liquors, respectively, wherein x is the concentration ratio of Na_2S to Na_2CO_3 in the green liquor calculated as g NaOH/l and y is the concentration ratio of Na_2S to total titratable alkali calculated as g NaOH/l.

7. A process as claimed in claim 2 or 3, wherein the improvement additionally comprises:

calculating the following, through measurements:
the carbonate conversion and Na_2CO_3 concentration of the green liquor, the carbonate conversion and NaOH concentration of the white liquor, and one or more of the active alkali and effective alkali concentrations of the white liquor; and

controlling the composition of the white liquor on the basis of such calculations.

8. A process as claimed in claim 4 or 5, wherein said quantities are x and y obtained by means of chemical analysis of the green and white liquors, respectively, wherein x is the concentration ratio of Na_2S to Na_2CO_3 in the green liquor calculated as g NaOH/l and y is the concentration ratio of Na_2S to total titratable alkali calculated as g NaOH/l; an additional improvement comprising:

calculating the following, through measurements:
the carbonate conversion and Na_2CO_3 concentration of the green liquor, the carbonate conversion and NaOH con-

mab/

centration of the white liquor, and one or more of the active alkali and effective alkali concentrations of the white liquor; and

controlling the composition of the white liquor on the basis of such calculations.

9. A process as claimed in claim 2 or 3, wherein the improvement additionally comprises:

calculating the following, through measurements:

the carbonate conversion and Na_2CO_3 concentration of the green liquor, the carbonate conversion and NaOH concentration of the white liquor, and one or more of the active alkali and effective alkali concentrations of the white liquor; and

controlling the composition of the white liquor on the basis of such calculations, and by the amount of burnt lime introduced into a slaker used in said process.

10. A process as claimed in claim 4 or 5, wherein said quantities are x and y obtained by means of chemical analysis of the green and white liquors, respectively, wherein x is the concentration ratio of Na_2S to Na_2CO_3 in the green liquor calculated as g NaOH/l and y is the concentration ratio of Na_2S to total titratable alkali calculated as g NaOH/l; and additional improvement comprising:

calculating the following, through measurements:

the carbonate conversion and Na_2CO_3 concentration of the green liquor, the carbonate conversion and NaOH concentration of the white liquor, and one or more of the

active alkali and effective alkali concentrations of the white liquor; and

controlling the composition of the white liquor on the basis of such calculations, and by the amount of burnt lime introduced into a slaker used in said process.

11. A process as claimed in claim 2 or 3, wherein the improvement additionally comprises:

calculating the following, through measurements:
the carbonate conversion and Na_2CO_3 concentration of the green liquor, the carbonate conversion and NaOH concentration of the white liquor, and one or more of the active alkali and effective alkali concentrations of the white liquor; and

controlling the composition of the white liquor on the basis of such calculations, and by regulating the total titratable alkali value of the green liquor.

12. A process as claimed in claim 4 or 5, wherein said quantities are x and y obtained by means of chemical analysis of the green and white liquors, respectively, wherein x is the concentration ratio of Na_2S to Na_2CO_3 in the green liquor calculated as g NaOH/l and y is the concentration ratio of Na_2S to total titratable alkali calculated as g NaOH/l; an additional improvement comprising:

calculating the following, through measurements:
the carbonate conversion and Na_2CO_3 concentration of the green liquor, the carbonate conversion and NaOH concentration of the white liquor, and one or more of the active alkali and effective alkali concentrations of the

mab/

white liquor; and

controlling the composition of the white liquor on the basis of such calculations, and by regulating the total titratable alkali value of the green liquor.

13. A process as claimed in claim 2 or 3, wherein the improvement additionally comprises:

calculating the following, through measurements:

the carbonate conversion and Na_2CO_3 concentration of the green liquor, the carbonate conversion and NaOH concentration of the white liquor, and one or more of the active alkali and effective alkali concentrations of the white liquor; and

controlling the composition of the white liquor on the basis of such calculations, by the amount of burnt lime introduced into a slaker used in said process, and by regulating the total titratable alkali value of the green liquor.

14. A process as claimed in claim 4 or 5, wherein said quantities are x and y obtained by means of chemical analysis of the green and white liquors, respectively, wherein x is the concentration ratio of Na_2S to Na_2CO_3 in the green liquor calculated as g NaOH/l and y is the concentration ratio of Na_2S to total titratable alkali calculated as g NaOH/l; an additional improvement comprising:

calculating the following, through measurements:

the carbonate conversion and Na_2CO_3 concentration of the green liquor, the carbonate conversion and NaOH concentration of the white liquor, and one or more of the

active alkali and effective alkali concentrations of the white liquor; and

controlling the composition of the white liquor on the basis of such calculations, by the amount of burnt lime introduced into a slaker used in said process, and by regulating the total titratable alkali value of the green liquor.

15. A process as claimed in claim 2 or 3, wherein the improvement additionally comprises:

calculating the following, through measurements:

the carbonate conversion and Na_2CO_3 concentration of the green liquor, the carbonate conversion and NaOH concentration of the white liquor, and one or more of the active alkali and effective alkali concentrations of the white liquor; and

controlling the composition of the white liquor on the basis of such calculations, and by regulating the total titratable alkali value of the green liquor;

wherein a small partial flow of the green liquor is transferred, with stirring, to a measuring vessel, similar to a slaker used in said process in such a manner that the volume ratio of the slaker to the measuring vessel is equal to the ratio of the respective amounts of green liquor fed thereto, wherein one or more of a conductivity measurement, and total titratable alkali value are determined at a corresponding place in the measuring vessel to the slaker, were the slaker to be used instead of the measuring vessel.

mab/

1198558

16. A process as claimed in claim 4 or 5, wherein said quantities are x and y obtained by means of chemical analysis of the green and white liquors, respectively, wherein x is the concentration ratio of Na_2S to Na_2CO_3 in the green liquor calculated as g NaOH/l and y is the concentration ratio of Na_2S to total titratable alkali calculated as g NaOH/l; an additional improvement comprising:

calculating the following, through measurements:

the carbonate conversion and Na_2CO_3 concentration of the green liquor, the carbonate conversion and NaOH concentration of the white liquor, and one or more of the active alkali and effective alkali concentrations of the white liquor; and

controlling the composition of the white liquor on the basis of such calculations, and by regulating the total titratable alkali value of the green liquor;

wherein a small partial flow of the green liquor is transferred, with stirring, to a measuring vessel, similar to a slaker used in said process in such a manner that the volume ratio of the slaker to the measuring vessel is equal to the ratio of the respective amounts of green liquor fed thereto, wherein one or more of a conductivity measurement, and total titratable alkali value are determined at a corresponding place in the measuring vessel to the slaker, were the slaker to be used instead of the measuring vessel.

17. A process as claimed in claim 2 or 3, wherein the improvement additionally comprises:

mab/

1198558

calculating the following, through measurements:
the carbonate conversion and Na_2CO_3 concentration
of the green liquor, the carbonate conversion and NaOH
concentration of the white liquor, and one or more of the
active alkali and effective alkali concentrations of the
white liquor; and

controlling the composition of the white liquor
on the basis of such calculations, by the amount of burnt
lime introduced into a slaker used in said process, and by
regulating the total titratable alkali value of the green
liquor;

wherein a small partial flow of the green liquor
is transferred, with stirring, to a measuring vessel,
similar to the slaker in such a manner that the volume ratio
of the slaker to the measuring vessel is equal to the ratio
of the respective amounts of green liquor fed thereto,
wherein one or more of a conductivity measurement, and
total titratable alkali value are determined at a corres-
ponding place in the measuring vessel to the slaker, were
the slaker to be used instead of the measuring vessel.

18. A process as claimed in claim 2 or 3,
wherein the improvement additionally comprises:

calculating the following, through measurements:
the carbonate conversion and Na_2CO_3 concentration
of the green liquor, the carbonate conversion and NaOH
concentration of the white liquor, and one or more of the
active alkali and effective alkali concentrations of the
white liquor; and

mab/

1198558

controlling the composition of the white liquor on the basis of such calculations, and by regulating the total titratable alkali value of the green liquor;

wherein a data processor is used for on-line registration of the measured values for calculating one or more of the following: the amount of burnt lime to be added to a slaker used in said process per unit time, the amount of green liquor to be added to the slaker per unit time, and the total titratable alkali value of the green liquor.

19. A process as claimed in claim 4 or 5, wherein said quantities are x and y obtained by means of chemical analysis of the green and white liquors, respectively, wherein x is the concentration ratio of Na_2S to Na_2CO_3 in the green liquor calculated as g NaOH/l and y is the concentration ratio of Na_2S to total titratable alkali calculated as g NaOH/l; an additional improvement comprising:

calculating the following, through measurements:

the carbonate conversion and Na_2CO_3 concentration of the green liquor, the carbonate conversion and NaOH concentration of the white liquor, and one or more of the active alkali and effective alkali concentrations of the white liquor; and

controlling the composition of the white liquor on the basis of such calculations, and by regulating the total titratable alkali value of the green liquor;

wherein a data processor is used for on-line registration of the measured values for calculating one

mab/

1198558

or more of the following: the amount of burnt lime to be added to a slaker used in said process per unit time, the amount of green liquor to be added to the slaker per unit time, and the total titratable alkali value of the green liquor.

20. A process as claimed in claim 2 or 3, wherein the improvement additionally comprises:

calculating the following, through measurements:

the carbonate conversion and Na_2CO_3 concentration of the green liquor, the carbonate conversion and NaOH concentration of the white liquor, and one or more of the active alkali and effective alkali concentrations of the white liquor; and

controlling the composition of the white liquor on the basis of such calculations, by the amount of burnt lime introduced into a slaker used in said process, and by regulating the total titratable alkali value of the green liquor;

wherein a data processor is used for on-line registration of the measured values for calculating one or more of the following: the amount of burnt lime to be added to the slaker per unit time, the amount of green liquor to be added to the slaker per unit time, and the total titratable alkali value of the green liquor.

21. A process as claimed in claim 2 or 3, wherein the improvement additionally comprises:

calculating the following, through measurements:

the carbonate conversion and Na_2CO_3 concentration of the green liquor, the carbonate conversion and NaOH

mab/

1198558

concentration of the white liquor, and one or more of the active alkali and effective alkali concentrations of the white liquor; and

controlling the composition of the white liquor on the basis of such calculations, and by regulating the total titratable alkali value of the green liquor;

wherein a small partial flow of the green liquor is transferred, with stirring, to a measuring vessel, similar to a slaker used in said process in such a manner that the volume ratio of the slaker to the measuring vessel is equal to the ratio of the respective amounts of green liquor fed thereto, wherein one or more of a conductivity measurement, and total titratable alkali value are determined at a corresponding place in the measuring vessel to the slaker, were the slaker to be used instead of the measuring vessel; and

wherein a data processor is used for on-line registration of the measured values for calculating one or more of the following: the amount of burnt lime to be added to the slaker per unit time, the amount of green liquor to be added to the slaker per unit time, and the total titratable alkali value of the green liquor.

22. A process as claimed in claim 4 or 5, wherein said quantities are x and y obtained by means of chemical analysis of the green and white liquors, respectively, wherein x is the concentration ratio of Na_2S to Na_2CO_3 in the green liquor calculated as g NaOH/l and y is the concentration ratio of Na_2S to total titratable alkali calculated as g NaOH/l; an additional improvement

mab/.

1198558

comprising:

calculating the following, through measurements:

the carbonate conversion and Na_2CO_3 concentration of the green liquor, the carbonate conversion and NaOH concentration of the white liquor, and one or more of the active alkali and effective alkali concentrations of the white liquor; and

controlling the composition of the white liquor on the basis of such calculations, and by regulating the total titratable alkali value of the green liquor;

wherein a small partial flow of the green liquor is transferred, with stirring, to a measuring vessel, similar to a slaker used in said process in such a manner that the volume ratio of the slaker to the measuring vessel is equal to the ratio of the respective amounts of green liquor fed thereto, wherein one or more of a conductivity measurement, and total titratable alkali value are determined at a corresponding place in the measuring vessel to the slaker, were the slaker to be used instead of the measuring vessel; and

wherein a data processor is used for on-line registration of the measured values for calculating one or more of the following: the amount of burnt lime to be added to the slaker per unit time, the amount of green liquor to be added to the slaker per unit time, and the total titratable alkali value of the green liquor.

23. A process as claimed in claim 2 or 3, wherein the improvement additionally comprises:

mab/

1198558

calculating the following, through measurements:

the carbonate conversion and Na_2CO_3 concentration of the green liquor, the carbonate conversion and NaOH concentration of the white liquor, and one or more of the active alkali and effective alkali concentrations of the white liquor; and

controlling the composition of the white liquor on the basis of such calculations, by the amount of burnt lime introduced into a slaker used in said process, and by regulating the total titratable alkali value of the green liquor;

wherein a small partial flow of the green liquor is transferred, with stirring, to a measuring vessel, similar to the slaker in such a manner that the volume ratio of the slaker to the measuring vessel is equal to the ratio of the respective amounts of green liquor fed thereto, wherein one or more of a conductivity measurement, and total titratable alkali value are determined at a corresponding place in the measuring vessel to the slaker, were the slaker to be used instead of the measuring vessel; and

wherein a data processor is used for on-line registration of the measured values for calculating one or more of the following: the amount of burnt lime to be added to the slaker per unit time, the amount of green liquor to be added to the slaker per unit time, and the total titratable alkali value of the green liquor.

24. A process as claimed in claim 2 or 3, wherein the improvement additionally comprises:

71
25

mab/

1198558

calculating the following, through measurements:

the carbonate conversion and Na_2CO_3 concentration of the green liquor, the carbonate conversion and NaOH concentration of the white liquor, and one or more of the active alkali and effective alkali concentrations of the white liquor; and

controlling the composition of the white liquor on the basis of such calculations, and by regulating the total titratable alkali value of the green liquor;

wherein the conductivity measurement after the termination of the causticization step is effected in one or more of the following: a slaker, a classifier, a following causticizer or outlet thereof, of a plant used for said process, and the clarified white liquor.

25. A process as claimed in claim 4 or 5, wherein said quantities are X and Y obtained by means of chemical analysis of the green and white liquors, respectively, wherein X is the concentration ratio of Na_2S to Na_2CO_3 in the green liquor calculated as g NaOH/l and Y is the concentration ratio of Na_2S to total titratable alkali calculated as g NaOH/l; an additional improvement comprising:

calculating the following, through measurements:

the carbonate conversion and Na_2CO_3 concentration of the green liquor, the carbonate conversion and NaOH concentration of the white liquor, and one or more of the active alkali and effective alkali concentrations of the white liquor; and

controlling the composition of the white liquor on the basis of such calculations, and by regulating the

mab/

total titratable alkali value of the green liquor;

wherein the conductivity measurement after the termination of the causticization step is effected in one or more of the following: a slaker, a classifier, a following causticizer or outlet thereof, of a plant used for said process, and the clarified white liquor.

26. A process as claimed in claim 2 or 3, wherein the improvement additionally comprises:

calculating the following, through measurements:
the carbonate conversion and Na_2CO_3 concentration of the green liquor, the carbonate conversion and NaOH concentration of the white liquor, and one or more of the active alkali and effective alkali concentrations of the white liquor; and

controlling the composition of the white liquor on the basis of such calculations, by the amount of burnt lime introduced into a slaker used in said process, and by regulating the total titratable alkali value of the green liquor;

wherein the conductivity measurement after the termination of the causticization step is effected in one or more of the following: the slaker, a classifier, a following causticizer or outlet thereof, of a plant used for said process, and the clarified white liquor.

27. A process as claimed in claim 2 or 3, wherein the improvement additionally comprises:

calculating the following, through measurements;
the carbonate conversion and Na_2CO_3 concentration of the green liquor, the carbonate conversion and NaOH

mab/

1198558

concentration of the white liquor, and one or more of the active alkali and effective alkali concentrations of the white liquor; and

controlling the composition of the white liquor on the basis of such calculations, and by regulating the total titratable alkali value of the green liquor;

wherein a small partial flow of the green liquor is transferred, with stirring, to a measuring vessel, similar to a slaker used in said process in such a manner that the volume ratio of the slaker to the measuring vessel is equal to the ratio of the respective amounts of green liquor fed thereto, wherein one or more of a conductivity measurement, and total titratable alkali value are determined at a corresponding place in the measuring vessel to the slaker, were the slaker to be used instead of the measuring vessel; and

wherein the conductivity measurement after the termination of the causticization step is effected in one or more of the following: the slaker, a classifier, a following causticizer or outlet thereof, of a plant used for said process, and the clarified white liquor.

28. A process as claimed in claim 4 or 5, wherein said quantities are x and y obtained by means of chemical analysis of the green and white liquors, respectively, wherein x is the concentration ratio of Na_2S to Na_2CO_3 in the green liquor calculated as g NaOH/l and y is the concentration ratio of Na_2S to total titratable alkali calculated as g NaOH/l; an additional improvement comprising:

mab/

1198558

calculating the following, through measurements:
the carbonate conversion and Na_2CO_3 concentration
of the green liquor, the carbonate conversion and NaOH
concentration of the white liquor, and one or more of the
active alkali and effective alkali concentrations of the
white liquor; and

controlling the composition of the white liquor
on the basis of such calculations, and by regulating the
total titratable alkali value of the green liquor;

wherein a small partial flow of the green liquor
is transferred, with stirring, to a measuring vessel,
similar to a slaker used in said process in such a manner
that the volume ratio of the slaker to the measuring vessel
is equal to the ratio of the respective amounts of green
liquor fed thereto, wherein one or more of a conductivity
measurement, and total titratable alkali value are determined
at a corresponding place in the measuring vessel to the
slaker, were the slaker to be used instead of the measuring
vessel; and

wherein the conductivity measurement after the
termination of the causticization step is effected in one
or more of the following: the slaker, a classifier, a
following causticizer or outlet thereof, of a plant used
for said process, and the clarified white liquor.

29. A process as claimed in claim 2 or 3,
wherein the improvement additionally comprises:

calculating the following, through measurements:
the carbonate conversion and Na_2CO_3 concentration
of the green liquor, the carbonate conversion and NaOH
concentration of the white liquor, and one or more of the

3
mab/

441

1198558

active alkali and effective alkali concentrations of the white liquor; and

controlling the composition of the white liquor on the basis of such calculations, by the amount of burnt lime introduced into a slaker used in said process, and by regulating the total titratable alkali value of the green liquor;

wherein a small partial flow of the green liquor is transferred, with stirring, to a measuring vessel, similar to the slaker in such a manner that the volume ratio of the slaker to the measuring vessel is equal to the ratio of the respective amounts of green liquor fed thereto, wherein one or more of a conductivity measurement, and total titratable alkali value are determined at a corresponding place in the measuring vessel to the slaker, were the slaker to be used instead of the measuring vessel; and

wherein the conductivity measurement after the termination of the causticization step is effected in one or more of the following: the slaker, a classifier, a following causticizer or outlet thereof, of a plant used for said process, and the clarified white liquor.

30. A process as claimed in claim 2 or 3, wherein the improvement additionally comprises:

calculating the following, through measurements:

the carbonate conversion and Na_2CO_3 concentration of the green liquor, the carbonate conversion and NaOH concentration of the white liquor, and one or more of the active alkali and effective alkali concentrations of the white liquor; and

mab/

1198558

controlling the composition of the white liquor on the basis of such calculations, and by regulating the total titratable alkali value of the green liquor;

wherein a data processor is used for on-line registration of the measured values for calculating one or more of the following: the amount of burnt lime to be added to a slaker used in said process per unit time, the amount of green liquor to be added to the slaker per unit time, and the total titratable alkali value of the green liquor; and

wherein the conductivity measurement after the termination of the causticization step is effected in one or more of the following: the slaker, a classifier, a following causticizer or outlet thereof, of a plant used for said process, and the clarified white liquor.

31. A process as claimed in claim 4 or 5, wherein said quantities are x and y obtained by means of chemical analysis of the green and white liquors, respectively, wherein x is the concentration ratio of Na_2S to Na_2CO_3 in the green liquor calculated as g NaOH/l and y is the concentration ratio of Na_2S to total titratable alkali calculated as g NaOH/l; an additional improvement comprising:

calculating the following, through measurements:

the carbonate conversion and Na_2CO_3 concentration of the green liquor, the carbonate conversion and NaOH concentration of the white liquor, and one or more of the active alkali and effective alkali concentrations of the white liquor; and

mab/

43

1198558

controlling the composition of the white liquor on the basis of such calculations, and by regulating the total titratable alkali value of the green liquor;

wherein a data processor is used for on-line registration of the measured values for calculating one or more of the following: the amount of burnt lime to be added to a slaker used in said process per unit time, the amount of green liquor to be added to the slaker per unit time, and the total titratable alkali value of the green liquor; and

wherein the conductivity measurement after the termination of the causticization step is effected in one or more of the following: the slaker, a classifier, a following causticizer or outlet thereof, of a plant used for said process, and the clarified white liquor.

32. A process as claimed in claim 2 or 3, wherein the improvement additionally comprises:

calculating the following, through measurements: the carbonate conversion and Na_2CO_3 concentration of the green liquor, the carbonate conversion and NaOH concentration of the white liquor, and one or more of the active alkali and effective alkali concentrations of the white liquor; and

controlling the composition of the white liquor on the basis of such calculations, by the amount of burnt lime introduced into a slaker used in said process, and by regulating the total titratable alkali value of the green liquor;

wherein a data processor is used for on-line

mab/

44

1198558

registration of the measured values for calculating one or more of the following: the amount of burnt lime to be added to the slaker per unit time, the amount of green liquor to be added to the slaker per unit time, and the total titratable alkali value of the green liquor; and

wherein the conductivity measurement after the termination of the causticization step is effected in one or more of the following: the slaker, a classifier, a following causticizer or outlet thereof, of a plant used for said process, and the clarified white liquor.

33. A process as claimed in claim 2 or 3, wherein the improvement additionally comprises:

calculating the following, through measurements:

the carbonate conversion and Na_2CO_3 concentration of the green liquor, the carbonate conversion and NaOH concentration of the white liquor, and one or more of the active alkali and effective alkali concentrations of the white liquor; and

controlling the composition of the white liquor on the basis of such calculations, and by regulating the total titratable alkali value of the green liquor;

wherein a small partial flow of the green liquor is transferred, with stirring, to a measuring vessel, similar to a slaker used in said process in such a manner that the volume ratio of the slaker to the measuring vessel is equal to the ratio of the respective amounts of green liquor fed thereto, wherein one or more of a conductivity measurement, and total titratable alkali value are determined at a corresponding place in the measuring vessel to the

mab/

45

1198558

slaker, where the slaker to be used instead of the measuring vessel;

wherein a data processor is used for on-line registration of the measured values for calculating one or more of the following: the amount of burnt lime to be added to the slaker per unit time, the amount of green liquor to be added to the slaker per unit time, and the total titratable alkali value of the green liquor; and

wherein the conductivity measurement after the termination of the causticization step is effected in one or more of the following: the slaker, a classifier, a following causticizer or outlet thereof, of a plant used for said process, and the clarified white liquor.

34. A process as claimed in claim 4 or 5, wherein said quantities are x and y obtained by means of chemical analysis of the green and white liquors, respectively, wherein x is the concentration ratio of Na_2S to Na_2CO_3 in the green liquor calculated as g NaOH/l and y is the concentration ratio of Na_2S to total titratable alkali calculated as g NaOH/l; an additional improvement comprising:

calculating the following, through measurements:
the carbonate conversion and Na_2CO_3 concentration of the green liquor, the carbonate conversion and NaOH concentration of the white liquor, and one or more of the active alkali and effective alkali concentrations of the white liquor; and

controlling the composition of the white liquor on the basis of such calculations, and by regulating the

mab/

1198558

total titratable alkali value of the green liquor;

wherein a small partial flow of the green liquor is transferred, with stirring, to a measuring vessel, similar to a slaker used in said process in such a manner that the volume ratio of the slaker to the measuring vessel is equal to the ratio of the respective amounts of green liquor fed thereto, wherein one or more of a conductivity measurement, and total titratable alkali value are determined at a corresponding place in the measuring vessel to the slaker, were the slaker to be used instead of the measuring vessel;

wherein a data processor is used for on-line registration of the measured values for calculating one or more of the following: the amount of burnt lime to be added to the slaker per unit time, the amount of green liquor to be added to the slaker per unit time, and the total titratable alkali value of the green liquor; and

wherein the conductivity measurement after the termination of the causticization step is effected in one or more of the following: the slaker, a classifier, a following causticizer or outlet thereof, of a plant used for said process, and the clarified white liquor.

35. A process as claimed in claim 2 or 3, wherein the improvement additionally comprises:

calculating the following, through measurements:

the carbonate conversion and Na_2CO_3 concentration of the green liquor, the carbonate conversion and NaOH concentration of the white liquor, and one or more of the active alkali and effective alkali concentrations of the

mab/

1198558

white liquor; and

controlling the composition of the white liquor on the basis of such calculations, by the amount of burnt lime introduced into a slaker used in said process, and by regulating the total titratable alkali value of the green liquor;

wherein a small partial flow of the green liquor is transferred, with stirring, to a measuring vessel, similar to the slaker in such a manner that the volume ratio of the slaker to the measuring vessel is equal to the ratio of the respective amounts of green liquor fed thereto, wherein one or more of a conductivity measurement, and total titratable alkali value are determined at a corresponding place in the measuring vessel to the slaker, were the slaker to be used instead of the measuring vessel;

wherein a data processor is used for on-line registration of the measured values for calculating one or more of the following: the amount of burnt lime to be added to the slaker per unit time, the amount of green liquor to be added to the slaker per unit time, and the total titratable alkali value of the green liquor; and

wherein the conductivity measurement after the termination of the causticization step is effected in one or more of the following: the slaker, a classifier, a following causticizer or outlet thereof, of a plant used for said process, and the clarified white liquor.

36. A process as claimed in claim 4 or 5, wherein said quantities are x and y obtained by means of chemical analysis of the green and white liquors,

mab/

1198558

respectively, wherein x is the concentration ratio of Na_2S to Na_2CO_3 in the green liquor calculated as g NaOH/l and y is the concentration ratio of Na_2S to total titratable alkali calculated as g NaOH/l; an additional improvement comprising:

calculating the following, through measurements:
the carbonate conversion and Na_2CO_3 concentration of the green liquor, the carbonate conversion and NaOH concentration of the white liquor, and one or more of the active alkali and effective alkali concentrations of the white liquor; and

controlling the composition of the white liquor on the basis of such calculations, by the amount of burnt lime introduced into a slaker used in said process, and by regulating the total titratable alkali value of the green liquor;

wherein a small partial flow of the green liquor is transferred, with stirring, to a measuring vessel, similar to a slaker used in said process in such a manner that the volume ratio of the slaker to the measuring vessel is equal to the ratio of the respective amounts of green liquor fed thereto, wherein one or more of a conductivity measurement, and total titratable alkali value are determined at a corresponding place in the measuring vessel to the slaker, were the slaker to be used instead of the measuring vessel.

37. A process as claimed in claim 4 or 5, wherein said quantities are x and y obtained by means of chemical analysis of the green and white liquors,

mab/

1198558

respectively, wherein x is the concentration ratio of Na_2S to Na_2CO_3 in the green liquor calculated as g NaOH/l and y is the concentration ratio of Na_2S to total titratable alkali calculated as g NaOH/l; an additional improvement comprising:

calculating the following, through measurements:
the carbonate conversion and Na_2CO_3 concentration of the green liquor, the carbonate conversion and NaOH concentration of the white liquor, and one or more of the active alkali and effective alkali concentrations of the white liquor; and

controlling the composition of the white liquor on the basis of such calculations, by the amount of burnt lime introduced into a slaker used in said process, and by regulating the total titratable alkali value of the green liquor;

wherein a data processor is used for on-line registration of the measured values for calculating one or more of the following: the amount of burnt lime to be added to a slaker used in said process per unit time, the amount of green liquor to be added to the slaker per unit time, and the total titratable alkali value of the green liquor.

38. A process as claimed in claim 4 or 5, wherein said quantities are x and y obtained by means of chemical analysis of the green and white liquors, respectively, wherein x is the concentration ratio of Na_2S to Na_2CO_3 in the green liquor calculated as g NaOH/l and y is the concentration ratio of Na_2S to total titratable

mab/

1198558

alkali calculated as g NaOH/l; an additional improvement comprising:

calculating the following, through measurements:

the carbonate conversion and Na_2CO_3 concentration of the green liquor, the carbonate conversion and NaOH concentration of the white liquor, and one or more of the active alkali and effective alkali concentrations of the white liquor; and

controlling the composition of the white liquor on the basis of such calculations, by the amount of burnt lime introduced into a slaker used in said process, and by regulating the total titratable alkali value of the green liquor;

wherein a small partial flow of the green liquor is transferred, with stirring, to a measuring vessel, similar to a slaker used in said process in such a manner that the volume ratio of the slaker to the measuring vessel is equal to the ratio of the respective amounts of green liquor fed thereto, wherein one or more of a conductivity measurement, and total titratable alkali value are determined at a corresponding place in the measuring vessel to the slaker, were the slaker to be used instead of the measuring vessel; and

wherein a data processor is used for on-line registration of the measured values for calculating one or more of the following: the amount of burnt lime to be added to the slaker per unit time, the amount of green liquor to be added to the slaker per unit time, and the total titratable alkali value of the green liquor.

39. A process as claimed in claim 4 or 5, wherein said quantities are x and y obtained by means of chemical analysis of the green and white liquors, respectively, wherein x is the concentration ratio of Na_2S to Na_2CO_3 in the green liquor calculated as g NaOH/l and y is the concentration ratio of Na_2S to total titratable alkali calculated as g NaOH/l; an additional improvement comprising:

calculating the following, through measurements: the carbonate conversion and Na_2CO_3 concentration of the green liquor, the carbonate conversion and NaOH concentration of the white liquor, and one or more of the active alkali and effective alkali concentrations of the white liquor; and

controlling the composition of the white liquor on the basis of such calculations, by the amount of burnt lime introduced into a slaker used in said process, and by regulating the total titratable alkali value of the green liquor;

wherein the conductivity measurement after the termination of the causticization step is effected in one or more of the following: a slaker, a classifier, a following causticizer or outlet thereof, of a plant used for said process, and the clarified white liquor.

40. A process as claimed in claim 4 or 5, wherein said quantities are x and y obtained by means of chemical analysis of the green and white liquors, respectively, wherein x is the concentration ratio of Na_2S to Na_2CO_3 in the green liquor calculated as g NaOH/l and y is the concentration ratio of Na_2S to total titratable

1198558

alkali calculated as g NaOH/l; an additional improvement comprising:

calculating the following, through measurements:
the carbonate conversion and Na_2CO_3 concentration of the green liquor, the carbonate conversion and NaOH concentration of the white liquor, and one or more of the active alkali and effective alkali concentrations of the white liquor; and

controlling the composition of the white liquor on the basis of such calculations, by the amount of burnt lime introduced into a slaker used in said process, and by regulating the total titratable alkali value of the green liquor;

wherein a small partial flow of the green liquor is transferred, with stirring, to a measuring vessel, similar to a slaker used in said process in such a manner that the volume ratio of the slaker to the measuring vessel is equal to the ratio of the respective amounts of green liquor fed thereto, wherein one or more of a conductivity measurement, and total titratable alkali value are determined at a corresponding place in the measuring vessel to the slaker, were the slaker to be used instead of the measuring vessel;

wherein the conductivity measurement after the termination of the causticization step is effected in one or more of the following: the slaker, a classifier, a following causticizer or outlet thereof, of a plant used for said process, and the clarified white liquor.

41. A process as claimed in claim 4 or 5, wherein said quantities are x and y obtained by means of

mab/

chemical analysis of the green and white liquors, respectively, wherein x is the concentration ratio of Na_2S to Na_2CO_3 in the green liquor calculated as g NaOH/l and y is the concentration ratio of Na_2S to total titratable alkali calculated as g NaOH/l; an additional improvement comprising:

calculating the following, through measurements:

the carbonate conversion and Na_2CO_3 concentration of the green liquor, the carbonate conversion and NaOH concentration of the white liquor, and one or more of the active alkali and effective alkali concentrations of the white liquor; and

controlling the composition of the white liquor on the basis of such calculations, by the amount of burnt lime introduced into a slaker used in said process, and by regulating the total titratable alkali value of the green liquor;

wherein a data processor is used for on-line registration of the measured values for calculating one or more of the following: the amount of burnt lime to be added to a slaker used in said process per unit time, the amount of green liquor to be added to the slaker per unit time, and the total titratable alkali value of the green liquor; and

wherein the conductivity measurement after the termination of the causticization step is effected in one or more of the following: the slaker, a classifier, a following causticizer or outlet thereof, of a plant used for said process, and the clarified white liquor.

1198558

42. A process as claimed in claim 4 or 5, wherein said quantities are x and y obtained by means of chemical analysis of the green and white liquors, respectively, wherein x is the concentration ratio of Na_2S to Na_2CO_3 in the green liquor calculated as g NaOH/l and y is the concentration ratio of Na_2S to total titratable alkali calculated as g NaOH/l; an additional improvement comprising:

calculating the following, through measurements:

the carbonate conversion and Na_2CO_3 concentration of the green liquor, the carbonate conversion and NaOH concentration of the white liquor, and one or more of the active alkali and effective alkali concentrations of the white liquor; and

controlling the composition of the white liquor on the basis of such calculations, by the amount of burnt lime introduced into a slaker used in said process, and by regulating the total titratable alkali value of the green liquor;

wherein a small partial flow of the green liquor is transferred, with stirring, to a measuring vessel, similar to a slaker used in said process in such a manner that the volume ratio of the slaker to the measuring vessel is equal to the ratio of the respective amounts of green liquor fed thereto, wherein one or more of a conductivity measurement, and total titratable alkali value are determined at a corresponding place in the measuring vessel to the slaker, were the slaker to be used instead of the measuring vessel; and

mab/

1198558

wherein a data processor is used for on-line registration of the measured values for calculating one or more of the following: the amount of burnt lime to be added to the slaker per unit time, the amount of green liquor to be added to the slaker per unit time, and the total titratable alkali value of the green liquor; and

wherein the conductivity measurement after the termination of the causticization step is effected in one or more of the following: the slaker, a classifier, a following causticizer or outlet thereof, of a plant used for said process, and the clarified white liquor.

43. A process for controlling the causticizing process of green liquor in the sulphate process, which produces an alkaline white liquor for pulping of wood, comprising:

(a) measuring immediately after the causticizing process the value of the electric conductivity of the white liquor formed thereby;

(b) measuring immediately before said causticizing process the value of the conductivity of the green liquor being fed into said process;

(c) numerically correlating the conductivity of said white liquor and said green liquor to obtain the reaction of carbonate value for said causticizing process by means of the equation:

$$\text{Reaction of Carbonate} = \frac{K_{Hv} - K_{Gr}}{F_1(TTA)}$$

wherein $F_1(TTA) = 4.694 \times 10^{-5} \times (TTA)^2 - 2.652 \times 10^{-2}(TTA) + 7.335$ ($\frac{mS/cm}{g/l}$)

wherein K_{Hv} and K_{Gr} are the conductivities of the white and green liquors, respectively, and TTA is the total titratable

mab/l/c

56

alkali of the green liquor; and

(d) adjusting the reaction of carbonate in said causticizing process based on the reaction of carbonate value obtained in step (c).

44. The process of claim 43, further comprising:

(e) measuring the value of the specific gravity of the green liquor to obtain the value of the total titratable alkali of said liquor.

45. The process of claim 43, wherein the value of the total titratable alkali of said green liquor is obtained by measuring the gamma ray absorption of said green liquor.

46. The process of claim 44, further comprising:

(f) chemically determining the value of the concentration of Na_2S and of Na_2CO_3 in said green liquor, to obtain the values x and y, wherein x is the ratio of the value of the concentrations of said Na_2S and said Na_2CO_3 expressed as g NaOH/l and y is the ratio of the value of the concentration of Na_2S in said white liquor and the value of said total alkali of said green liquor expressed as g NaOH/l; and

(g) then using said x and y values in step (d) for adjusting the reaction of carbonate in said causticizing process.

47. The process of claim 44, further comprising:

(f) measuring the value of the specific gravity of said green liquor to obtain the value of the total alkali of said liquor;

1198558

(g) correlating the specific gravity, the electrical conductivity and the total alkali of said white and said green liquors to obtain the value for the content of Na_2CO_3 and NaOH in the green liquor, the degree of reaction of carbonate in the causticizing process and the content of NaOH, the content of active alkali, the content of effective alkali, the degree of causticizing and the sulphidity in the white liquor; and

(h) then using one or more of said values in step (d) for adjusting the reaction of carbonate in said causticizing process.

48. The process of claim 43, further comprising:

(e) constantly removing a small part of the green liquor immediately prior to entering a slaker, wherein said causticizing process begins; and

(f) transferring said part to a vessel thereof, whereby a further measurement of the conductivity of said green liquor can be made, the volume ratio of said vessel to said slaker being equal to the volume ratio of the respective parts of green liquor fed thereto.

49. The process of claim 44, further comprising:

(f) on-line transferring said measured value of specific gravity to a data processor to calculate the degree of adjusting of the reaction of carbonate of step (d) per unit time.

50. The process of claim 44, wherein step (d) is carried out by adjusting the amount of quick lime, the value of the total alkali or the amount of the green liquor, or a combination thereof being fed per unit time to a slaker, wherein said causticizing process begins.

mab/

51. The process of claim 44, further comprising:

(f) constantly removing a small part of the green liquor immediately prior to entering a slaker, wherein said causticizing process begins; and

(g) transferring said part to a vessel thereof, whereby a further measurement of one or more of the conductivity and the specific gravity of said green liquor can be made, the volume ratio of said vessel to said slaker being equal to the volume ratio of the respective parts of green liquor fed thereto.

52. The process of claim 43, further comprising:

(e) on-line transferring said measured values obtained in steps (a) and (b) to a data processor to calculate the degree of adjusting of the reaction of carbonate of step (d) per unit time.

53. The process of claim 43, wherein step (d)

is carried out by adjusting the amount of quick lime, or the amount of the green liquor, or a combination thereof, being fed per unit time to a slaker, wherein said causticizing process begins.

54. The process of claim 43, wherein the con-

ductivity of said white liquor of step (a) is measured within a slaker, wherein said causticization process begins, within one or more causticizers, whereto the partially causticized white liquor is transferred therefrom at the outlet of one or more of the causticizers, whereby the causticized white liquor is discharged from said causticizers, or a combination thereof.

1198558

55. The process of claim 44, wherein the conductivity of said white liquor of step (a) is measured within a slaker, wherein said causticization process begins, within one or more causticizers, whereto the partially causticized white liquor is transferred therefrom, at the outlet of one or more of the causticizers, whersby the causticized white liquor is discharged from said causticizers, or a combination thereof.

mab/lc

